

BITUMEN GRADE 60/70

ITEMS	TYPICAL SPECIFICATION (60/70)
Specific Gravity @ 25/25	1.01/1.06
Penetration @ 25	60/70
Softening Point	45/59
Ductility @ 25	100MIN
Loss on Heating (WT) %	0.2 MAX
Drop in Penetration after heating %	20 MAX
Flash Point C	250 MIN
Solubility CS2 (WT) %	99.5 MIN
Organic matter insoluble in CS2 (WT) %	-----
SPOT TEST	Negative