

PRODUCT DATA SHEET

PC0712 PLYCARBONATE

Application: Suitable for Molding and Extrusion

Typical Sales Specification

SR. NO.	PROPERTY	CONDITION	UNIT	TEST METHOD	VALUE
(A) General Property					
1	Density	g/cm ³	ASTM D-792	1.20
2	Melt Flow Rate (MFR)	@300 C 1.2 Kgs load	g/10mins	ASTM D-1238	7.1-12.0
(B) Mechanical Property					
3	Tensile Strength	@Yield	Mpa	ASTM D-638	≥ 60
4	Tensile Stress	@Yield	Mpa	ASTM D-638	60-70
5	Elongation Strain	@Break	%	ASTM D-638	≥ 90
6	Modulus Of Elasticity	Mpa	ASTM D-638	2200-2400
7	Charpy Impact Strength	Notched	Kj/m ²	ASTM D-256	≥ 25
8	Ball Indentation Hardness		N/mm ²	DIN 53456	≥103
(C) Electrical Property					
9	Di- Electric Strength	@ 50 Hz Diameter-50 mm Thickness- 2mm	Kv/mm	ASTM D-149	≥ 20
10	Di- Electric Constant	@ 1 MHz	ASTM D-150	2.8-3.1
11	Loss Index	@ 1 MHz	ASTM D-150	0.008-0.011
12	Loss Index	@ 50 MHz	ASTM D-150	0.0008-0.001
(D) Thermanal Property					
13	Vicat Softening Temperature	50N,50 C/h	C	ASTM D-1525	145-150
(E) Optical Property					
14	Transmittance	@Thinckness 2mm	%	ASTM D-1003	≥ 80
15	Solvent Content		ppm	GC	500 max